

# Material

## 75 FKM 585

black-brown

cross linking: bisphenolically

<b>revision index</b>	<b>revision date</b>	<b>page</b>	1 / 3
13	7/12/2022		

Physical properties	nominal range	typical values	
<b>Density</b> DIN EN ISO 1183-1	2.05 ±0.03	2.05	g/cm <sup>3</sup>
<b>Hardness</b> DIN ISO 7619-1	75 ±5	75	Shore
<b>Rebound resilience</b> DIN 53512	---	6	%
<b>Modulus</b> 100 %, DIN 53504, S2	> 4	6.9	MPa
<b>Tensile strength</b> DIN 53504, S2	> 10	12.8	MPa
<b>Elongation at break</b> DIN 53504, S2	> 175	225	%
<b>Compression set</b> DIN ISO 815, 22 h, 175 °C	---	28	%
<b>Low Temperature</b> DIN 53765, DSC	---	-14	°C
<b>Temperature range</b>	-30°C to 200°C		

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

Country	Part	Remark	Expires
ADI Free		see certificate	see DoC
Info ROHS and ELV		EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC
PFOA / PFOS free		see certificate	see DoC

**Freudenberg**  
Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: MaterialCompliance@fst.com



**Material**  
**75 FKM 585**

black-brown

cross linking: bisphenolically

**revision index**  
13

**revision date**  
7/12/2022

**page** 2 / 3

**Tested after ASTM D 2000: M 2 HK 710 A1-10 B37 B38 EF31 EO78 Z1**

		<b>nominal range</b>	<b>typical values</b>
Hardness	Shore	70 ±5	74
Tensile strength	MPa	min. 10	12.5
Elongation at break	%	min. 175	240
<b>A1-10 Change after aging in Air 70h/250°C</b>			
Hardness	Shore A	10	1
Tensile strength	%	-25	2
Elongation at break	%	-25	18
<b>B37 Compression set 22h/175°C</b>	%	50	29
<b>B38 Compression set 22h/200°C</b>	%	50	40
<b>EF31 Change after aging in Fuel C 70h/23°C</b>			
Hardness	Shore	±5	-1
Tensile strength	%	-25	-10
Elongation at break	%	-20	40
Volume	%	0 to 10	2
<b>EO78 Change after aging in Fluid No. 101 70h/200°C</b>			
Hardness	Shore	-15 to 5	-4
Tensile strength	%	-40	-10
Elongation at break	%	-20	35
Volume	%	0 to 15	7
<b>Z1 Low Temperature DIN 53765, DSC</b>	°C	---	-14

**Freudenberg**

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: MaterialCompliance@fst.com



## Material

### 75 FKM 585

black-brown

cross linking: bisphenolically

**revision index**

13

**revision date**

7/12/2022

**page** 3 / 3

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

**Freudenberg**

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)

