

Technical data sheet in accordance with ASTM

# Material

## FKM FP603401

brown

cross linking: bisphenolically

**revision index**

3

**revision date**

8/23/2022

**page**

1 / 3

### Physical properties

	<b>nominal range</b>	<b>typical values</b>	
<b>Density</b> ASTM D297	1.98 ±0.02	1.98	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D2240, Shore A	60 ±5	59	Shore
<b>Tensile strength</b> ASTM D412	---	10.6	MPa
<b>Elongation at break</b> ASTM D412	---	291	%
<b>Compression set</b> ASTM D395, Slab B, 22 h, 200 °C	---	12	%

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	<b>Country</b>	<b>Part</b>	<b>Remark</b>	<b>Expires</b>
ADI Free Info ROHS and ELV			see certificate EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC see DoC

### Change after aging in Air: 70h/250°C

		<b>Typ. values</b>		
		Base value	After aging	difference
Hardness (ASTM D573, Shore A)	Shore	59	60	1
Tensile strength (ASTM D573)	MPa	10.6	11.4	8 %
Elongation at break (ASTM D573)	%	291	267.7	-8 %

### Change after aging in ASTM service fluid # 101: 70h/200°C

		<b>Typ. values</b>		
		Base value	After aging	difference
Hardness (ASTM D471, Shore A)	Shore	59	52	-7
Tensile strength (ASTM D471)	MPa	10.6	10.4	-2 %
Elongation at break (ASTM D471)	%	291	317.1	9 %
volume change (ASTM D471)	%		12	

### Freudenberg

Freudenberg Industrial Services GmbH  
 Global Material Technology  
 Nadja Güldner

Telefon: -  
 Fax: -  
 Email: FIS.Compound.CRC@fst.com



Technical data sheet in accordance with ASTM

## Material

### FKM FP603401

brown

cross linking: bisphenolically

#### revision index

3

#### revision date

8/23/2022

page 2 / 3

#### Change after aging in Fuel C: 70h/23°C

#### Typ. values

Hardness (ASTM D471, Shore A)  
Tensile strength (ASTM D471)  
Elongation at break (ASTM D471)  
volume change (ASTM D471)

	Base value	After aging	difference
Shore	59	56	-3
MPa	10.6	8.5	-20 %
%	291	264.8	-9 %
%		4	

### Freudenberg

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner

Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com



Technical data sheet in accordance with ASTM

## **Material**

### **FKM FP603401**

brown

cross linking: bisphenolically

**revision index**

3

**revision date**

8/23/2022

**page**

3 / 3

### **No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### **Freudenberg**

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner

Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com

